

GROWTH OF METASTABLE HIGH-ORDER COMMENSURATE OVERLAYERS OF Pb ON Cu(001)

Wei Li and Gianfranco Vidali

Department of Physics, Syracuse University, Syracuse, NY 13244-1130 USA

ABSTRACT

We studied the growth and ordering of a Pb layer deposited on Cu(001) at 150 K. Contrary to the case of adsorption of Pb at room temperature, islands readily form. These islands order in a high-order commensurate structure of symmetry $(\sqrt{61} \times \sqrt{61})R\text{tan}^{-1}\left(\frac{5}{6}\right)$. We followed the growth of these islands using atom beam scattering. From the measurement of the island diffraction peak profiles we found a power growth law for the mean island- size versus coverage. Upon increasing the coverage another high-order commensurate structure is formed, $(5 \times 5)R\text{tan}^{-1}\left(\frac{3}{4}\right)$. All the ordered phases obtained by adsorption at low temperature are metastable.

I. INTRODUCTION

The study of growth and ordering of overlayers deposited on cold single crystal substrates poses special challenges. Recent experimental [1, 2] and computational work [3] on growth of metal overlayers on metal substrates has shown that our understanding of the interplay of kinetic, dynamic and energetic processes during growth is inadequate. Of the many metal-on metal systems [4], particularly interesting is the study of lattice mismatched combinations. In these systems, ordered layers are the results of a competition of entropic terms as well as of adsorbate-substrate and adsorbate-adsorbate interactions. The absence of strongly directional bonds and of well tested interaction potentials makes it difficult to carry out reliable calculations about epitaxial processes.

Within this contest, we found that the study of the growth and ordered phases of Pb on Cu(001) at low temperature can yield some valuable insights and a few surprises as well. This is a lattice mismatched system (bulk lattice constant of Cu=3.6 Å, 4.5 Å for Pb) which has been extensively investigated in the past, but only for depositions on substrates at room temperature or higher (410 K) [5]. A preliminary report [2] of a study of adsorption of Pb at 150 K showed the appearance, near one layer coverage, of a high-order commensurate structure with 16 atoms per unit supercell (A unit supercell is the smallest cell commensurate with the lattice). An intriguing observation about this phase was that the proposed structure of the Pb layer had square symmetry (The supercell has also square symmetry). This is surprising, since it is usually believed that, for this type of metal-on-metal systems, high-order commensurate or incommensurate phases prefer hexagonal or quasi-hexagonal symmetries, since these have the highest coordination number [6].

Finally, we mention the work of Zuo and Wendelken [7]; investigating the growth of ordered islands of Ag on Si(111) with High Resolution LEED (HRLEED), they found

that the size distribution of island is self-similar. From an analysis of peak profiles, they found that the mean island size grows with increasing coverage as Θ^n . The value of the exponent n (0.20 to 0.35) was found dependent of the substrate temperature during deposition (350 to 450 °C).

II. EXPERIMENTAL

The apparatus consists of a helium beam scattering line (18.4 meV incident energy, velocity resolution $\delta v/v \sim 1\%$ at 1200 PSI) coupled to a UHV chamber [8]. In the UHV chamber there are located: a liquid nitrogen cooled Knudsen evaporation source, a 4-grid LEED-Auger optics and a helium beam detector, which is a differentially pumped quadrupole mass spectrometer with an aperture of 0.5° . This spectrometer can be rotated around the axis of the sample manipulator and can be positioned to measure the reflected helium beam during Pb deposition [8]. The deposition time for one monolayer of Pb was typically about 38 minutes. The coverage calibration was obtained from Auger experiment as well as an analysis of the high temperature ordered phases. Shorter deposition times did not affect the results. Although the layers deposited at 150 K were found to be metastable (see below), there was no indication from ABS, LEED or Auger of a rearrangement within the layer during measurements.

The thoroughly desulfurized copper sample was cleaned prior to each run by Ar ion sputtering and annealing at 580°C. Helium beam scattering was used to assess the quality of the prepared surface as in previous studies [2, 8].

III. RESULTS

In Fig.1 we present a sketch of the phase diagram. The phases below 0°C are metastable in the sense that they are obtained by depositing Pb at 150 K and cannot be reached by cooling the overlayer deposited at room temperature. In Fig.2 the LEED pattern and proposed structure of $(\sqrt{61} \times \sqrt{61})R\text{tan}^{-1}\left(\frac{5}{6}\right)$ are presented. The

$(\sqrt{61} \times \sqrt{61})\text{Rtan}^{-1}\left(\frac{5}{6}\right)$ structure, with an ideal coverage of 0.49, was deduced from He beam scattering data and from coverage considerations [9]. The $(5 \times 5)\text{Rtan}^{-1}\left(\frac{3}{4}\right)$ structure has been shown elsewhere [2, 10].

At low coverage, Pb aggregates in islands with a $(\sqrt{61} \times \sqrt{61})\text{Rtan}^{-1}\left(\frac{5}{6}\right)$ supercell; the evolution of the specular and diffraction peak profiles gives information on how islands grow. Each diffraction peak was fitted with the convolution of the instrument response function (well approximated by a Gaussian) and a fitting function. Following analyses of island growth studied by HRLEED, we tried Gaussian, Lorentzian and power Lorentzian as fitting functions [6, 11]. In Fig.3, fits using a power Lorentzian:

$$I(\Delta K_{\parallel}) \propto \frac{1}{(\xi^2 + \Delta K_{\parallel}^2)^m} \quad (1)$$

with $m=5$ are presented for three different coverages. The same fitting function with $m=5$ was used for all coverages, from about 0.1ML to 0.5ML. The inverse width of the deconvolved peak (FWHM of Eq.(1)) is displayed as a function of coverage in Fig.4. The growth of the mean island size $\bar{R}$ versus coverage can be well described by the equation:

$$\bar{R} \sim \frac{1}{FWHM} \propto \Theta^n \quad (2)$$

The average size of ordered islands goes from about $30\text{\AA}$ to $80\text{\AA}$. We also performed an independent analysis of the diffraction beam shapes. Each data set was deconvolved of the instrument response function using Fourier analysis. Notice that these deconvolved data have been obtained without assuming any functional form for the "true" signal. In Fig. 5 we superimposed deconvolved data from three different coverages after scaling the horizontal axis. The fact that their shape is the same indicates that growth is self-similar in the range of coverage investigated. The oscillations in the wings of the peaks are due to the deconvolution procedures; in fact, they are not present in the original data, see Fig. 3.

IV. DISCUSSION

The two ordered phases obtained after deposition at 150K are metastable; upon heating them above about 0°C they convert to the phases obtained by depositing Pb at 400 K. These latter ones are equilibrium phases, since they can be melted and recrystallized [2, 9]. The metastable phases have quite a different structure than the equilibrium ones, since they are in registry with the substrate via very large supercells. Only one atom in 16 for the $(5 \times 5)R\text{tan}^{-1}\left(\frac{3}{4}\right)$ or 30 for the $(\sqrt{61} \times \sqrt{61})R\text{tan}^{-1}\left(\frac{5}{6}\right)$ is in registry of the substrate, indicating that they are the results of limited diffusion and of a delicate competition between Pb-Pb and Pb-Cu interactions. It is unusual to find structures with so few atoms in registry with the substrate; in fact, in most cases the overlayer structure becomes incommensurate with a hexagonal unit cell. A calculation of the energetics of these phases is in progress and will be reported elsewhere.

We found that the distribution of island size is self-similar, see Fig.5, that is the peak profiles can be superimposed after a rescaling of the horizontal axis. For the case of growth of two-dimensional islands, we are not aware of any theory that makes a prediction about the exponent in Eq.(2) [12]. It is not known the shape of the universal function describing the distribution of island sizes; Eq.(1) should be considered at this stage as a convenient fitting function. The value of the exponent we obtained is different from the ones of Ref. 7. In that case, the highest exponent, 0.35, has been obtained for the highest substrate temperature, 450 °C. At this stage it is too premature to speculate whether the values of n can be grouped in universality classes. The temperature dependence of n might indicate that different processes are activated at different temperatures. Because of technical limitations we are not able at the present time to obtain information on the temperature dependence of n for our system.

ACKNOWLEDGMENTS

This work was supported by NSF grant DMR 8802512.

References

- [1] R.Kunkel, B. Poelsema, L. K. Verheij and G. Comsa, Phys. Rev. Lett. 65 (1990) 733; W.F.Engelhoff, Jr. and I.Jacob, Phys. Rev. Lett. 62 (1989) 921.
- [2] Wei Li, J.-S.Lin, M.Karimi, C.Moses, and G.Vidali, J. Vac. Sci. Technol. A9 (1991) 1707.
- [3] D.E.Sanders and A.E.DePristo, Surf. Sci. 254 (1991) 341.
- [4] E. Bauer, in: Structure and Dynamics of Surfaces II, Eds. W.Schommers and P.Von Blanchenhagen, Topics in Current Physics Vol.43 (Springer Verlag, 1987) p.115.
- [5] A.Sepulveda and G.E.Rhead, Surf. Sci. 66 (1977) 436; A.Sánchez and S.Ferrer, Phys. Rev. B 39 (1989) 5778.
- [6] R.Diehl, in: Phase Transitions in Surface Films 2, NATO ASI Series B267, Eds. H.Taub, G.Torzo, H.J.Lauter, and S.C.Fain, Jr. (Plenum Press, New York, 1991) p.99.
- [7] J.-K.Zuo and J.F.Wendelken, Phys. Rev. Lett. 66 (1991) 2227.
- [8] G.Vidali, Wei Li, J.-S. Lin, and C.Moses, Mat. Res. Soc. Symp. Proc. 208 (1991) 99; Wei Li, J.-S.Lin, M.Karimi, C.Moses, and G.Vidali, Appl. Surf. Sci. 48/49 (1991) 160.
- [9] Wei Li and G. Vidali, in preparation.
- [10] O.Biham, L.-W.Chen, W.Chen, and G.Vidali, Proceedings of ICss-8, this volume.
- [11] J.-K.Zuo, G.-C.Wang, and T.-M.Lu, Phys. Rev. B 40 (1989) 524.

[12] P.Meakin, Rep. Prog. Phys. 55 (1992) 115.

FIGURE CAPTIONS

Figure 1. Sketch of phase diagram of Pb on Cu(001) obtained by ABS and LEED data.

Crossed region: disordered; cross-hatched region: phases coexist.

Figure 2. Reciprocal space (left) and proposed real space structure (right) of $(\sqrt{61} \times \sqrt{61})R\text{tan}^{-1}\left(\frac{5}{6}\right)$.

Figure 3. (0,-1) ABS diffraction peak from $(\sqrt{61} \times \sqrt{61})R\text{tan}^{-1}\left(\frac{5}{6}\right)$ islands at representative coverages; Solid lines are the fitting results of the convolution of the instrument response function with the function in Eq.(1). $\theta_i=60^\circ$.

Figure 4. Inverse FWHM vs. coverage obtained from an analysis of diffraction peaks as in Fig.3. The line is the best-fit through the data, see Eq.(2).

Figure 5. ABS diffraction data from islands after deconvolution of the instrument response function. Data from three coverages have been rescaled and plot in the same graph. $\theta_i=60^\circ$. w is the peak full width at half maximum (FWHM).